

**AMENDMENTS TO THE CLAIMS:**

The listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (Currently Amended) Method for determining the storage state of an ammonia-adsorbing SCR catalyst having at least one channel for receiving gas flow, wherein the change in at least one physical property of the SCR catalyst changes on account of the  $\text{NH}_3$  storing process, said method comprising:

applying a measuring pickup to at least one surface of said at least one channel of said the SCR catalyst;

sensing an electrical impedance of the SCR catalyst from said measuring pickup wherein the sensing of the impedance takes place at one or more frequencies from the frequency range between 0 Hz and an upper cut-off frequency, at which the wavelength corresponding to the measuring frequency is significantly less than the dimensions of the measuring ~~arrangement~~ pickup; and

determining the storage state of the SCR catalyst on the basis of said electrical impedance.

2. (Previously Presented) Method according to claim 1, wherein the sensing of the electrical impedance is carried out at a plurality of points of the SCR catalyst.

3-5. (Cancelled)

6. (Previously Presented) Method according to claim 1, wherein the sensing of the electrical impedance occurs with either two electrodes, a conductor loop, or an inter-digital structure.

7. (Previously Presented) Method according to claim 2, wherein one of said plurality of points is near the inlet of the SCR catalyst, and another of said plurality of points is disposed in the rearward quarter of the SCR catalyst.

8-9. (Cancelled)

10. (Currently Amended) Method for determining the storage state of an ammonia-adsorbing SCR catalyst, said SCR catalyst adapted for use in an exhaust gas stream, said method comprising:

placing a material identical or similar to the SCR catalyst material with regard to its physical properties, said material being arranged in the exhaust-gas stream in addition to the SCR catalyst, ~~said material being arranged in the exhaust-gas stream in addition to the SCR catalyst~~, said material includes at least one physical property that changes with the  $\text{NH}_3$  storing process;

applying said material to a measuring pickup;

sensing an electrical impedance of said material from said measuring pickup wherein the sensing of the impedance takes place at one or more frequencies from the frequency range between 0 Hz, i.e. d.c. voltage, and an upper cut-off frequency, at which the wavelength corresponding to the measuring frequency is significantly less than the dimensions of the measuring arrangement; and

determining the storage state on the basis of said electrical impedance.

11. (Previously Presented) Method according to claim 10, wherein the sensing of the electrical impedance property is carried out at a plurality of points of the SCR catalyst.

12-14. (Cancelled)

15. (Withdrawn) Apparatus for carrying out the method according to claim 14, wherein the measuring pickup for sensing the complex electrical impedance includes a substrate having two generally flat sides, on one flat side either a conductor or electrode structure is applied, and on the other flat side an electrical heater is applied, the material being applied on the flat side that is provided with the conductor or electrode structure.

16. (Withdrawn) Apparatus according to claim 15, wherein either the conductor or electrode structure is an inter-digital structure.

17. (Withdrawn) Apparatus according to claim 16, wherein the substrate is selected from silicon, quartz or a ceramic, and the electrical heater has 100 nm to 50  $\mu$ m thick sheets of metal, and the conductor or electrode structure is constructed of metal and has a layer thickness of between 100 nm and 100  $\mu$ m and the material has a layer thickness of between 100 nm and 1000  $\mu$ m

18. (Cancelled)

19. (Withdrawn) Apparatus for carrying out the method according to Claim 18, wherein the measuring pickup for sensing the thermal electromotive force includes a substrate having two generally flat sides, on one flat side an electrical heater is applied on the other flat side the material and at least two pairs of thermocouples are applied.

20. (Withdrawn) Apparatus according to claim 19, wherein the substrate consists of silicon, quartz or a ceramic, and the electrical heater has 100 nm to 100  $\mu$ m thick sheets of metal.

21. (Cancelled)

22. (Withdrawn) Apparatus for carrying out the method according to Claim 21, wherein the measuring pickup for sensing the change in mass of the material includes a vibrating quartz crystal on which electrical excitation electrodes are applied on both sides, the material being applied at least on one excitation electrode.

23. (Withdrawn) Apparatus for carrying out the method according to claim 21, wherein the measuring pickup for recording the change in mass of the substitute material is constructed as follows: the laminar substitute material forms within a surface wave sensor the propagation path of a surface wave.

24. (Currently Amended) Method for determining the storage state of an ammonia-adsorbing SCR catalyst having at least one channel for receiving gas flow, wherein the change in at least one physical property of the SCR catalyst changes on account of an  $\text{NH}_3$  storing process, said method comprising:

applying a measuring pickup to at least one surface of said at least one channel the SCR catalyst;

sensing one of a thermal electromotive force of the SCR catalyst and the SCR catalysts' response to temperature changes, said sensing being provided by said measuring pickup; and

determining the storage state on the basis of said one of said thermal electromotive force and the catalysts' response to temperature changes.

25. (Previously Presented) The method according to claim 24, wherein the sensing is carried out at a plurality of points of the SCR catalyst.

26. (Previously Presented) The method according to claim 25, wherein one of said plurality of points is near an inlet of the SCR catalyst, and another one of said plurality of points is disposed in the rearward quarter of the SCR catalyst.

Serial No. 09/608,761  
Amendment Dated: July 20, 2004  
Reply to Office Action: March 24, 2004

**AMENDMENTS TO THE DRAWINGS:**

*The attached sheet of drawings includes changes to Fig. 1-4 and  
5a-5b with the replacement sheets attached.*